

TWA.8(60)-180(80)-32-310

TYPE Ø ANGLE LENGTH STEP LENGTH ALLOY

A L S R

 \emptyset 6 mm T = 13 mm \emptyset 8 mm T = 13 mm \emptyset 10 mm T = 15 mm





 $R = 4 \times \emptyset$

Anchors are manufactured with a DIN EN 10278 (DIN 671) cold drawn wire, by robots using hydraulic tools. That allows minimizing bend marking and avoids micro cracks


Our recommendations:

- The bent foot allows easier 90° positioning on steel casing and makes welding longer / stronger
- Always cap your anchors, it will give a small space into which the thermal expansion steel alloy (higher than castable) can move without creating stress and possibly damaging in the castable.




France – phone : + 33 3 66 50 00 30 anchorscontact@gmail.com www.anchorsforrefractorv.com






TWM.8(60)-180(80)-32-304

TYPE Ø ANGLE LENGTH STEP LENGTH ALLOY
A L S R





 $R = 4 \times \emptyset$

Anchors are manufactured with a DIN EN 10278 (DIN 671) cold drawn wire, by robots using hydraulic tools. That allows minimizing bend marking and avoids micro cracks


Our recommendations:


- The bent foot allows easier 90° positioning on steel casing and makes welding longer / stronger
- Always cap your anchors, it will give a small space into which the thermal expansion steel alloy (higher than castable) can move without creating stress and possibly damaging in the castable.



France – phone : + 33 3 66 50 00 30 anchorscontact@gmail.com www.anchorsforrefractorv.com


Options:






TWU.8(60)-160(80)-32-310

TYPE Ø ANGLE LENGTH STEP LENGTH ALLOY S R Α






Our recommendations:


- The bent foot allows easier 90° positioning on steel casing and makes welding longer / stronger
- Always cap your anchors, it will give a small space into which the thermal expansion steel alloy (higher than castable) can move without creating stress and possibly damaging in the castable.



France – phone: + 33 3 66 50 00 30 anchorscontact@gmail.com www.anchorsforrefractory.com









TWS.10(60)-220(110)-40-330

TYPE Ø ANGLE LENGTH STEP LENGTH ALLOY

A L S R





 $R = 4 \times \emptyset$

Anchors are manufactured with a DIN EN 10278 (DIN 671) cold drawn wire, by robots using hydraulic tools. That allows minimizing bend marking and avoids micro cracks


Our recommendations:


- The bent foot allows easier 90° positioning on steel casing and makes welding longer / stronger
- Always cap your anchors, it will give a small space into which the thermal expansion steel alloy (higher than castable) can move without creating stress and possibly damaging in the castable.



France – phone : + 33 3 66 50 00 30 anchorscontact@gmail.com www.anchorsforrefractorv.com








TWSS.10(90)-300(150-50)-40-330

TYPE Ø ANGLE LENGTH STEP – S LENGTH ALLOY
A L S1 R



 $R = 4 \times \emptyset$

Anchors are manufactured with a DIN EN 10278 (DIN 671) cold drawn wire, by robots using hydraulic tools. That allows minimizing bend marking and avoids micro cracks

Our recommendations:

- The bent foot allows easier 90° positioning on steel casing and makes welding longer / stronger
- Always cap your anchors, it will give a small space into which the thermal expansion steel alloy (higher than castable) can move without creating stress and possibly damaging in the castable.
- The straight down part is also corrugated, that improves anchoring of a backup guned insulating concrete layer



France – phone : + 33 3 66 50 00 30 anchorscontact@gmail.com www.anchorsforrefractorv.com

